

POLYSTICK® MX

SELF-ADHERED HIGH TEMP UNDERLAYMENT

PRODUCT DESCRIPTION

Polystick MX is a self-adhered high-temp waterproofing underlayment for metal roof coverings and various other applications. Utilizing ADESO® dual-compound self-adhered technology, Polystick MX features a polymer modified bitumen upper compound and a proprietary self-adhesive SBS (elastomeric) compound on the bottom. A split release film that protects the self-adhesive compound allows for easy application.

Polystick MX features a cavitated slip-resistant top film surface which can be exposed up to 90 days. With a temperature resistance of up to 250°F, Polystick MX is ideally suited for high temperature roof covering systems such as steel and aluminum panels.

TYPICAL APPLICATIONS

- Specifically designed as underlayment for high-temperature applications under metal
- Suitable for application under asphalt shingles and other approved roof coverings
- Over entire roof and/or for valleys, skylights and other critical areas

FEATURES AND BENEFITS

- ADESO dual-compound self-adhered technology
- Cavitated slip-resistant film surface with up to 90 days UV exposure
- Fiberglass reinforced for added strength and dimensional stability
- Self-adhered technology increases labor efficiency and roof dry-in speed
- Asphaltic compound provides excellent sealability around nails
- Approved up to 250°F

TECHNICAL DESCRIPTION*

Physical Properties	ASTM Method	ASTM Value
Maximum Load, Longitudinal and Transverse, min, kN/m (lbf/in.)	D5147	4.4 (25)
Elongation at break, min of modified bitumen portion (%)	D5147	10
Tear Resistance, Longitudinal and Transverse, min, N (lbf)	D5147	89 (20)
Moisture Vapor Permeability, max, perms	E96	0.1
Adhesion to Plywood @ 40°F, min, lbf/ft width	D1970	2.0
Adhesion to Plywood @ 75°F, min, lbf/ft width	D1970	12.0
Sealability around nail	D1970	pass
Waterproof integrity after low temp flexibility	D1970	pass
Waterproof integrity of lap seam	D1970	pass
Slip Resistance	D1970	pass

*The properties in this table are "as manufactured" unless otherwise noted.



PRODUCT DATA**

Net Coverage (Approx) ...200 ft² (18.5 m²)
 Gross Coverage215 ft² (20 m²)
 Weight (Approx) 68 lbs (30.8 kg)
 Thickness (Nominal) 50 mils (1.3 mm)
 Roll Size65'10" × 39 3/8" (20 m × 1 m)
 Rolls/Pallet.....30

**All values are nominal at time of manufacturing

APPLICABLE STANDARDS

- ASTM D1970
- UL Classified
- ICC ESR-1697 (Pending)
- Florida Building Code (Pending)
- Texas Department of Insurance (Pending)



PRODUCT CODES

- PSMX



www.polyglass.us

POLYSTICK® MX

SELF-ADHERED HIGH TEMP UNDERLAYMENT

APPLICATION INSTRUCTIONS

- Polystick MX may be applied directly to the roof deck where allowable by Code, or to various approved substrates such as Polyanchor HV nailable anchor sheet and Polytherm insulation. For additional substrate requirements and information refer to Polyglass published "Suitable Substrates for Self-Adhered (SA) Membranes."
- Do not apply directly on to existing shingles or other roof coverings.
- Apply only when the substrate is dry and project related temperatures (air, roof deck, membrane) are 40° F and rising.
- Be sure to follow all local building code recommendations and requirements with regards to the width of ice dam materials.
- If full roof coverage application is desired, proper venting of the structure is recommended. Consult a design professional for proper venting requirements. Applications involving nonventilated attics or sheathing with radiant barriers, an anchor sheet is recommended to allow venting and prevent the creation of a double vapor barrier condition.
- In steep slope applications where back nailing is required, be sure that all nails are covered by the overlapping next sheet.
- Polystick MX must be covered within 90 days of installation or unless otherwise limited by the Authority Having Jurisdiction.

MEMBRANE INSTALLATION

- Cut the Polystick MX to a suitable, workable length prior to placement.
- Lay the material flat in place, starting at the lowest point. Overlap seams 3" at black side lap area and a minimum 6" at end laps.
- Peel half of the release film from the roll and apply, firm even pressure from the center to the outer edge. Remove the backing from the remaining half of the roll and apply pressure.
- After adhering the Polystick underlayment, uniform pressure must be applied to the entire surface. Roll area with a 35 lbs or 75 lbs weighted roller, or water-filled lawn roller. Brooming the surface of the Polystick membrane is also acceptable on steep pitched roof applications where safety is a concern. NOTE: Polyglass advises that proper safety precautions are taken during rolling on all sloped roofs.

MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Waco, TX
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.us

General Line: (888) 410-1375
(954) 233-1330
Customer Service: (800) 222-9782
Technical Service: (866) 794-9659

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 1 year.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control. For most current product data and warranty information, visit www.polyglass.us.